

TELATA STANDARD

SBR


✓ Adatta per usi correnti.


IMPIEGO

Adatta per usi correnti ove non siano richieste particolari resistenze ad agenti atmosferici, oli e calore.

Superficie: Liscia/Liscia


1,5 gr/cm³

-25°C / +70°C

mm	STOCK	m	m
1,5	1 ✓	1,2/1,4	10
2	1 ✓	1,2/1,4/1,5	10
2,5	1 ✓	1,2/1,4	10
3	1 ✓	1,2/1,4/1,5	10
4	1 ✓	1,2/1,4/1,5	10
4	2 ✓	1,2/1,4/1,5	10
5	2 ✓	1,2/1,4/1,5	10
6/8	2 ✓	1,2/1,4	10
10	2 ✓	1,2/1,4	5/10
12 ÷ 20	2 ✓	1,2	5
25 ÷ 50	2 -	1	1


DUREZZA

 Norme
ASTM D2240

70 Shore A ± 5


CARICO ROTTURA

 Norme
ASTM D412

 40 kg/cm²

ALLUNGAMENTO

 Norme
ASTM D412

200%

Gimatec s.r.l

 Via Lago di Misurina, 59
36015 SCHIO (VI)

www.gimatec.com

Tel. 0445 314128

commerciale@gimatec.com